



▲ PF/FS: order code MAB - SB/FS: order code MAC

NEW MAMBO



NEW MAMBO

LANO

My kind of carpet!

lano carpets residential

| | | | | | | | |
|--|--|--|--|--|-------------------------------------|--|--|
| Fabricagemethode Technique de fabrication Manufacturing process Herstellungsart Tecnica di fabbricazione | tufted, 1/10" cut pile | Poolsamenstelling Nature du velours Pile composition Polmaterial Composizione felpa | PA | Tuftdoek Premier dossier Primary backing Trägermaterial Tela di supporto | woven | Rugtype Envers Secondary backing Rücken Sottofondo | PF/FS SB/FS |
| Totale dikte Hauteur totale Total height Gesamthöhe Spessore totale | PF/FS ± 7,0 mm SB/FS ± 6,0 mm | Nuttige poolhoogte Hauteur de velours utile Effective pile height Tatsächliche Florhöhe Spessore felpa utile | ± 4,0 mm | Breedte Largeur Width Breite Altezza | ± 400 cm | Aantal noppen/m ² Nombre de points/m ² Number of knots/sqm Noppenzahl/m ² Numero di punti/mq | ± 204880 |
| Poolinzetgewicht/m ² Poids mis en oeuvre/m ² Pile weight/sqm Poleinsatzgewicht/m ² Peso felpa/mq | ± 450 gr | Totaal gewicht/m ² Poids total/m ² Total weight/sqm Gesamtgewicht/m ² Peso totale/mq | PF/FS 1650 gr SB/FS 1520 gr | EN 13501-1 Brandgedrag Comportement au feu Fire behaviour Brennverhalten Reazione al fuoco | C_{fi}-s1 | EN 1307-2004 Classificatie Classification Classificazione Klassifizierung Classificazione | Class 22+ Domestic General Class 31 Commercial Moderate |
| ISO 105 B02 2000 Lichtechtheid Solidité à la lumière Lightfastness Lichtechtheid Solidità colori alla luce | ≥ 5-6 | ISO 105 E01 2002 Waterechtheid verkleuring Solidité à l'eau changement couleur Waterfastness change in colour Wasserechtheit Änderung der Farbe Solidità colori all'acqua cambio colore | ≥ 4 | ISO 105 E01 2002 Waterechtheid uitbloeding Solidité à l'eau dégorgement Waterfastness staining Wasserechtheit anbluten Solidità colori all'acqua sfumatura colore | ≥ 3-4 | ISO 105 X12 2001 Wrijftechtheid droog Solidité au frottement sec Rubbingfastness dry Reibungechtheit trocken Solidità colori allo sfregamento a secco | ≥ 4-5 |
| ISO 105 X12 2001 Wrijftechtheid nat Solidité au frottement humide Rubbingfastness wet Reibungechtheit nass Solidità colori allo sfregamento umido | ≥ 4-5 | ISO 140/8 1997 Contactgeluidsisolatie Isolation aux bruits d'impact Impact sound insulation Trittschallverbesserungsmaß Miglioramento acustico | PF/FS ± 28 dB | ISO 354 Geluidsdempingsvermogen α _s Absorption phonique α _s Sound absorption α _s Schallabsorptionsgrad α _s Grado d'assorbimento acustico α _s | PF/FS ± 0,53 1000 Hz | ISO 354 Geluidsdempingsvermogen α _w Absorption phonique α _w Sound absorption α _w Schallabsorptionsgrad α _w Grado d'assorbimento acustico α _w | PF/FS ± 0,25 |
| DIN 52612 Warmteoorlaatweerstand Résistivité thermique Thermal retention Wärmedurchlaßwiderstand Resistenza termica | SB/FS ± 0,07 m²/kW | TOG rating | SB/FS ± 0,7 | | | | |

(±) These details are approximate. Complete specification details and associated certificates together with tolerances applying to the above can be provided upon request. We reserve the right to improve technical specifications without prior notice. Due to method of manufacture perfect pattern and/or colour matching cannot be guaranteed. In cut-pile carpeting, in rare cases, shading/pile reversal may occur without affecting its fitness for use. Shading/pile reversal can not be considered as a manufacturing or a material defect and will not affect the durability of the carpet.

For other languages see: www.lano.com

PF/FS
REG.NR
364DCFF6
www.pro-dis.info

SB/FS
REG.NR
DC64DBAD
www.pro-dis.info

CE
0493-CPD-0020
EN 14041
C_{fl}-s1
DS
EN 1307

100% PA
ISO 9001
U₂₅P₂E₁C₀ 04/156

CE
0493-CPD-0016
EN 14041
C_{fl}-s1
DS
EN 1307

100% PA
ISO 9001

Lano - Zuidstraat 44
8530 Harelbeke-Belgium
t +32-56-65 40 00
f +32-56-65 40 09
marketing@lano.be
www.lano.com

The Green signature
of Lano Carpets

REACH
The new EU chemicals legislation